



STEDRANT TECHNOCLINIC PVT. LTD.

(Construction Materials Testing Laboratory)

Lab: # 39/5, Govardhan Garden, J C Industrial Area, Yelechenahalli, off. Kanakapura Main Road,
Bangalore - 560062. Ph.: 080 26860348. E-mail : labblr@stedrant.com CIN: U74999KA2017PTC100477
GST No.: 29AA YCS1231L1ZQ www.stedrant.com

DOC: STPL/RF/05/SPL
Ref: STPL/SPL/BLR/525/4/2023/5/S
Job Order dated: 29.04.2023

Page 1 of 1
Date: 22.03.2024

M/s. Pronil Building Products
XII, Aringnur, Annanagar,
Co-operative Nagar, Thiruvankodu
Chennai - 600077



TEST REPORT ON ACRYLLIC SWELLABLE BAR SAMPLE



Source of sample : Sample supplied by the customer
Date of receipt of the test sample : 20.02.2024
Customer's Reference : Letter dated 20.02.2024
UIN : 2307403
Project : Not Furnished
Sample Description # : PRONIL ACR
Period of test : 21.02.2024 to 21.03.2024
Condition of sample : Satisfactory

Sl. No.	Test Conducted		Test Results				Test Method
			@ 1 day	@ 3 day	@ 7 day	@ 28 day	
1	Volume change (%)	With Tap water	64.0	741.0	897.1	283.7	Laboratory development method
		With 5% NaCl	60.90	77.9	86.3	99.0	
2	Mass Change (%)	With Tap water	162.5	526.5	610.0	201.5	Laboratory development method
		With 5% NaCl	30.7	54.7	67.0	72.0	

As furnished by the customer.

- Note:**
1. The results relate only to the samples tested.
 2. Report shall not be reproduced, except in full, without the written approval of the lab.
 3. Any correction invalidates this report.

for **STEDRANT TECHNOCLINIC PVT LTD.**


22/3/24
 Mr. Radhakrishna
STPL Manager-Lab

End of the report

(Soil and Material Testing, Designs, Restoration and Non Destructive Testing Services)

Corporate Office :
"Sunvak Pride" # 95, Model House Street, Basavanagudi,
Bangalore - 560 004. Ph: 080 26629992

Hyderabad Off./ Lab :
Shed No. F-3/A, Street No. 10, IDA, Nacharam, Hyderabad - 500076.
Mob: +91 9000085790, +91 9000095790, +91 9908875790, +91 9908065790